

FORM PTO-1390 (REV. 11-2000)		U.S. DEPARTMENT OF COMMERCE PATENT AND TRADEMARK OFFICE		ATTORNEY'S DOCKET NUMBER CUK-051	
TRANSMITTAL LETTER TO THE UNITED STATES DESIGNATED/ELECTED OFFICE (DO/EO/US) CONCERNING A FILING UNDER 35 U.S.C. 371				U.S. APPLICATION NO. (If known, see 37 CFR 1.5) 09/937545	
INTERNATIONAL APPLICATION NO. PCT/GB00/01186		INTERNATIONAL FILING DATE 28 MARCH 2000		PRIORITY DATE CLAIMED 29 MARCH 1999	
TITLE OF INVENTION STOP-OFF FOR DIFFUSION COATING					
APPLICANT(S) FOR DO/EO/US					
Applicant herewith submits to the United States Designated/Elected Office (DO/EO/US) the following items and other information:					
1. <input checked="" type="checkbox"/> This is a FIRST submission of items concerning a filing under 35 U.S.C. 371. 2. <input type="checkbox"/> This is a SECOND or SUBSEQUENT submission of items concerning a filing under 35 U.S.C. 371. 3. <input checked="" type="checkbox"/> This is an express request to begin national examination procedures (35 U.S.C. 371(f)). The submission must include items (5), (6), (9) and (21) indicated below. 4. <input checked="" type="checkbox"/> The US has been elected by the expiration of 19 months from the priority date (Article 31). 5. <input checked="" type="checkbox"/> A copy of the International Application as filed (35 U.S.C. 371(c)(2)) a. <input checked="" type="checkbox"/> is attached hereto (required only if not communicated by the International Bureau). b. <input checked="" type="checkbox"/> has been communicated by the International Bureau. c. <input type="checkbox"/> is not required, as the application was filed in the United States Receiving Office (RO/US). 6. <input type="checkbox"/> An English language translation of the International Application as filed (35 U.S.C. 371(c)(2)). a. <input type="checkbox"/> is attached hereto. b. <input type="checkbox"/> has been previously submitted under 35 U.S.C. 154(d)(4). 7. <input checked="" type="checkbox"/> Amendments to the claims of the International Application under PCT Article 19 (35 U.S.C. 371(c)(3)) a. <input type="checkbox"/> are attached hereto (required only if not communicated by the International Bureau). b. <input type="checkbox"/> have been communicated by the International Bureau. c. <input type="checkbox"/> have not been made; however, the time limit for making such amendments has NOT expired. d. <input checked="" type="checkbox"/> have not been made and will not be made. 8. <input type="checkbox"/> An English language translation of the amendments to the claims under PCT Article 19 (35 U.S.C. 371 (c)(3)). 9. <input type="checkbox"/> An oath or declaration of the inventor(s) (35 U.S.C. 371(c)(4)). 10. <input type="checkbox"/> An English language translation of the annexes of the International Preliminary Examination Report under PCT Article 36 (35 U.S.C. 371(c)(5)). Items 11 to 20 below concern document(s) or information included: 11. <input checked="" type="checkbox"/> An Information Disclosure Statement under 37 CFR 1.97 and 1.98. 12. <input type="checkbox"/> An assignment document for recording. A separate cover sheet in compliance with 37 CFR 3.28 and 3.31 is included. 13. <input checked="" type="checkbox"/> A FIRST preliminary amendment. 14. <input type="checkbox"/> A SECOND or SUBSEQUENT preliminary amendment. 15. <input type="checkbox"/> A substitute specification. 16. <input type="checkbox"/> A change of power of attorney and/or address letter. 17. <input type="checkbox"/> A computer-readable form of the sequence listing in accordance with PCT Rule 13ter.2 and 35 U.S.C. 1.821 - 1.825. 18. <input type="checkbox"/> A second copy of the published international application under 35 U.S.C. 154(d)(4). 19. <input type="checkbox"/> A second copy of the English language translation of the international application under 35 U.S.C. 154(d)(4). 20. <input checked="" type="checkbox"/> Other items or information: 1. Copy of International Preliminary Examination Report 2. Copy of Form PCT/IB/304 3. Copy of Form PCT/IB/301					

U.S. APPLICATION NO. 09/937345 INTERNATIONAL APPLICATION NO. PCT/GB00/01186	ATTORNEY'S DOCKET NUMBER CUK-051
--	-------------------------------------

21. <input checked="" type="checkbox"/> The following fees are submitted: BASIC NATIONAL FEE (37 CFR 1.492 (a) (1) - (5)): Neither international preliminary examination fee (37 CFR 1.482) nor international search fee (37 CFR 1.445(a)(2)) paid to USPTO and International Search Report not prepared by the EPO or JPO. \$1000.00 International preliminary examination fee (37 CFR 1.482) not paid to USPTO but International Search Report prepared by the EPO or JPO \$860.00 International preliminary examination fee (37 CFR 1.482) not paid to USPTO but international search fee (37 CFR 1.445(a)(2)) paid to USPTO \$710.00 International preliminary examination fee (37 CFR 1.482) paid to USPTO but all claims did not satisfy provisions of PCT Article 33(1)-(4) \$690.00 International preliminary examination fee (37 CFR 1.482) paid to USPTO and all claims satisfied provisions of PCT Article 33(1)-(4) \$100.00 ENTER APPROPRIATE BASIC FEE AMOUNT =	CALCULATIONS PTO USE ONLY <table border="1" style="width: 100%; border-collapse: collapse;"> <tr> <td style="width: 50%; text-align: right;">\$ 860.00</td> <td style="width: 50%;"></td> </tr> <tr> <td style="text-align: right;">\$ 130.00</td> <td></td> </tr> </table>	\$ 860.00		\$ 130.00	
\$ 860.00					
\$ 130.00					

Surcharge of \$130.00 for furnishing the oath or declaration later than <input type="checkbox"/> 20 <input checked="" type="checkbox"/> 30 months from the earliest claimed priority date (37 CFR 1.492(e)).				\$	
CLAIMS	NUMBER FILED	NUMBER EXTRA	RATE	\$	
Total claims	- 20 =		x \$18.00	\$	0
Independent claims	- 3 =		x \$80.00	\$	0
MULTIPLE DEPENDENT CLAIM(S) (if applicable)				+ \$270.00	\$
TOTAL OF ABOVE CALCULATIONS =				\$	990.00
<input type="checkbox"/> Applicant claims small entity status. See 37 CFR 1.27. The fees indicated above are reduced by 1/2.				\$	
SUBTOTAL =				\$	
Processing fee of \$130.00 for furnishing the English translation later than <input type="checkbox"/> 20 <input type="checkbox"/> 30 months from the earliest claimed priority date (37 CFR 1.492(f)).				\$	
TOTAL NATIONAL FEE =				\$	990.00
Fee for recording the enclosed assignment (37 CFR 1.21(h)). The assignment must be accompanied by an appropriate cover sheet (37 CFR 3.28, 3.31). \$40.00 per property +				\$	
TOTAL FEES ENCLOSED =				\$	990.00
				Amount to be refunded:	\$
				charged:	\$

a. ☒ A check in the amount of \$ 990.00 to cover the above fees is enclosed.

b. ☐ Please charge my Deposit Account No. _____ in the amount of \$ _____ to cover the above fees.
 A duplicate copy of this sheet is enclosed.


c. ☒ The Commissioner is hereby authorized to charge any additional fees which may be required, or credit any
 overpayment to Deposit Account No. 19-4970. A duplicate copy of this sheet is enclosed.

d. ☐ Fees are to be charged to a credit card. **WARNING:** Information on this form may become public. **Credit card
 information should not be included on this form.** Provide credit card information and authorization on PTO-2038.

**NOTE: Where an appropriate time limit under 37 CFR 1.494 or 1.495 has not been met, a petition to revive (37 CFR
 1.137 (a) or (b)) must be filed and granted to restore the application to pending status.**

SEND ALL CORRESPONDENCE TO:

Mitchell D. Bittman
 Sequa Corporation
 3 University Plaza
 Hackensack, NJ 07601


 SIGNATURE

Mitchell D. Bittman
 NAME

27517
 REGISTRATION NUMBER

09/937545 PAT

JC09 Rec'd PCT/PTO 26 SEP 2001

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In Re Application Of: Hardy et al.)
Serial No.: To Be Assigned) Before the Examiner:
National Phase of PCT/GB00/01186)
International Filing Date)
28 March 2000) Group Art Unit:
For: Stop-Off For Diffusion)
Coating)

PRELIMINARY AMENDMENT

Honorable Commissioner of Patents and Trademarks
Box PCT
Washington, DC 20231


Dear Sir:

Applicants respectfully request that the following preliminary amendment be entered before examination of the subject application and calculation of the fees for filing the national phase of subject PCT patent application.

Enclosed please find:

1. A mark-up of Claim 1-26 showing the changes made (including the deletion of Claims 20-26).
2. A clean version of remaining Claims 1-19.

Respectfully submitted,



Mitchell D. Bittman
Registration Nº 27,517
Attorney for Applicants
Sequa Corporation
Three University Plaza
Hackensack, New Jersey 07601
(201) 343-1122 Ext. 2207

CLAIMS

1. A mask suitable for protecting a portion of a substrate surface against diffusion coating of the substrate by metallic vapours during a pack or vapour coating process which mask comprises a composite material containing silica and an inert refractory diluent and a metal or metal alloy, wherein the metal or metal alloy is one which is capable of reacting with silicon thereby preventing siliconisation of the substrate with silicon from the composite material under conditions of diffusion coating and which is capable of reacting with the metal being applied by diffusion coating thereby preventing diffusion coating of the portion of the substrate surface it is desired to protect.
2. A mask according to claim 1, wherein the metal or metal alloy is present in the composite material in an amount of 5 to 50% by weight based on the total weight of the mask.
3. A mask according to claim 2, wherein the metal or metal alloy is present in the ceramic in an amount of 10 to 20% by weight based on the total weight of the mask.
4. A mask according to [any one of the preceding claims] claim 2, wherein the metal is selected from nickel, cobalt, chromium, molybdenum and tungsten.
5. A mask according to claim 4, wherein the metal is nickel.
6. A mask according to [any one of claims 1 to 3] claim 2, wherein the metal alloy is an alloy based on a combination of metals selected from nickel, cobalt, chromium, aluminium, molybdenum, tungsten, vanadium, tantalum, titanium and hafnium.
7. A mask according to claim 6, wherein the metal alloy is a nickel-chromium alloy.
8. A mask according to [any one of the preceding claims] claim 2, wherein the inert refractory diluent comprises alumina, aluminosilicate or feldspar.
9. A mask according to claim 8, wherein the composite material comprises an aluminosilicate ceramic.
10. A mask according to [any one of claims 1 to 5] claim 5, which comprises from 10 to 20% by weight nickel dispersed in an aluminosilicate ceramic matrix.
11. A mask according to [any one of the preceding claims] claim 1 in the form of a diffusion coating cap.

12. A process for preparing a mask as defined in [any one of claims 1 to 10] claim 1, which process comprises mixing the metal or metal alloy with a ceramic material containing silica and an inert refractory diluent material, shaping the resultant mixture into a desired configuration to form a blank, and then either:

5 (a) firing the blank in a reducing atmosphere to prevent oxidation of the metal or metal alloy; or

(b) firing the blank in an oxidising atmosphere followed by treatment in a reducing atmosphere to reduce the metal or metal alloy.

10 13. A process according to claim 12, wherein the blank is in the shape of a cap.

14. A process according to claim 12 [or 13], wherein in (a) the blank is fired at a temperature of from 1150 to 1300°C for from 30 minutes to 3 hours at temperature.

15 15. A process according to claim 12 [or 13], wherein in (b) the blank is fired in an oxidising atmosphere at a temperature of from 1150 to 1300°C for from 30 minutes to 3 hours at temperature followed by treatment in a reducing atmosphere at a temperature of from 900 to 1200°C for a period of at least 1 hour.

20 16. A process for diffusion coating with a metal a selected portion of a substrate surface, which process comprises masking the substrate surface except for the portion to be coated with a mask as defined in [any one of claims 1 to 11] claim 1, subjecting the substrate to diffusion coating with the metallic vapour, and removing the mask from the substrate surface.

17. A process according to claim 16, wherein the metal which is being applied by diffusion coating is aluminium or chromium.

25 18. A process according to claim 16 [or 17], wherein the substrate is a turbine blade and the portion of the blade protected against diffusion coating is the blade root.

19. Use of a mask as defined in [any one of claims 1 to 11] claim 1, to protect the surface of a substrate in a diffusion coating process.

30 [20. A mixture suitable for use in preparing a mask as claimed in claim 1, which mixture is as defined in claim 12.]

[21. A mask according to claim 1 substantially as hereinbefore described with reference to any of the foregoing Examples.]

35 [22. A process according to claim 12, substantially as hereinbefore described with reference to any of the foregoing Examples.]

[23. A mask according to claim 1, when prepared by a process as claimed in any one of claims 12 to 15 or 22.]

[24. A diffusion coating process according to claim 16, substantially as hereinbefore described with reference to any of the foregoing Examples.]

5 [25. Use according to claim 19, substantially as hereinbefore described.]

[26. A mixture according to claim 20, substantially as hereinbefore described.]

CLAIMS

1. A mask suitable for protecting a portion of a substrate surface against diffusion coating of the substrate by metallic vapours during a pack or vapour coating process which mask comprises a composite material containing silica and an inert refractory diluent and a metal or metal alloy, wherein the metal or metal alloy is one which is capable of reacting with silicon thereby preventing siliconisation of the substrate with silicon from the composite material under conditions of diffusion coating and which is capable of reacting with the metal being applied by diffusion coating thereby preventing diffusion coating of the portion of the substrate surface it is desired to protect.
2. A mask according to claim 1, wherein the metal or metal alloy is present in the composite material in an amount of 5 to 50% by weight based on the total weight of the mask.
3. A mask according to claim 2, wherein the metal or metal alloy is present in the ceramic in an amount of 10 to 20% by weight based on the total weight of the mask.
4. A mask according to claim 2, wherein the metal is selected from nickel, cobalt, chromium, molybdenum and tungsten.
5. A mask according to claim 4, wherein the metal is nickel.
6. A mask according to claim 2, wherein the metal alloy is an alloy based on a combination of metals selected from nickel, cobalt, chromium, aluminium, molybdenum, tungsten, vanadium, tantalum, titanium and hafnium.
7. A mask according to claim 6, wherein the metal alloy is a nickel-chromium alloy.
8. A mask according to claim 2, wherein the inert refractory diluent comprises alumina, aluminosilicate or feldspar.
9. A mask according to claim 8, wherein the composite material comprises an aluminosilicate ceramic.
10. A mask according to claim 5, which comprises from 10 to 20% by weight nickel dispersed in an aluminosilicate ceramic matrix.
11. A mask according to claim 1 in the form of a diffusion coating cap.
12. A process for preparing a mask as defined in claim 1, which process comprises mixing the metal or metal alloy with a ceramic material containing silica and an inert refractory diluent material, shaping the resultant mixture into a desired configuration to form a blank, and then either:

(a) firing the blank in a reducing atmosphere to prevent oxidation of the metal or metal alloy; or

(b) firing the blank in an oxidising atmosphere followed by treatment in a reducing atmosphere to reduce the metal or metal alloy.

13. A process according to claim 12, wherein the blank is in the shape of a cap.

14. A process according to claim 12, wherein in (a) the blank is fired at a temperature of from 1150 to 1300°C for from 30 minutes to 3 hours at temperature.

15. A process according to claim 12, wherein in (b) the blank is fired in an oxidising atmosphere at a temperature of from 1150 to 1300°C for from 30 minutes to 3 hours at temperature followed by treatment in a reducing atmosphere at a temperature of from 900 to 1200°C for a period of at least 1 hour.

16. A process for diffusion coating with a metal a selected portion of a substrate surface, which process comprises masking the substrate surface except for the portion to be coated with a mask as defined in claim 1, subjecting the substrate to diffusion coating with the metallic vapour, and removing the mask from the substrate surface.

17. A process according to claim 16, wherein the metal which is being applied by diffusion coating is aluminium or chromium.

18. A process according to claim 16, wherein the substrate is a turbine blade and the portion of the blade protected against diffusion coating is the blade root.

19. Use of a mask as defined in claim 1, to protect the surface of a substrate in a diffusion coating process.

09/937545

WO 00/58531

2/PATS

PCT/GB00/01186

-1-

JC09 Rec'd PCT/PTO 26 SEP 2001

STOP-OFF FOR DIFFUSION COATING

The present invention relates to a mask for use in diffusion coating, to its preparation and its use in a diffusion coating process. The invention further relates to a composition/mixture of components suitable for use in preparing the mask.

5 Diffusion coating of substrate surfaces, such as high temperature superalloys, to introduce metal into the substrate surface, is typically carried out at high temperatures. Under coating conditions the metal which it is desired to introduce pervades to all substrate surfaces unless special precautions are taken to prevent this. Indeed, in many applications, it is important to restrict coating of the substrate to
10 certain areas. For example, when the substrate is a jet engine turbine blade, it is important that the turbine roots remain uncoated if mounting dimension tolerances are to be maintained.

A number of methods of masking a substrate surface to prevent diffusion coating have been proposed. Some methods involve the preparation and application
15 of stop-off pastes, slurries or resins. These are typically metal loaded compositions in which the metal serves to react with the metallic coating vapours, thereby preventing metal deposition in unwanted areas. The use of this kind of masking technique is labour and time intensive and requires the careful application of the composition to that area of the substrate to be protected, followed by drying of the
20 composition. Often a number of layers of composition need to be applied before diffusion coating. After coating, the mask must be fractured and removed. In this respect, the use of such stop-off compositions is also uneconomical due to their "one off" usage. It has also been observed that the compositions tend to exhibit reduced effectiveness at higher coating temperatures: at elevated temperatures components of
25 the mask composition can interact with the substrate surface to the detriment of the metallurgy of the component.

As an alternative, it has also been proposed to use plain (non metal-containing) ceramic caps to shield substrate surfaces. Silica based ceramic materials have been used previously. These have the benefit that they may be re-usable but
30 are only effective at lower temperature range short cycle processes because of the danger of siliconisation of the protected area of the substrate due to silicon in the ceramic.

The present invention seeks to overcome these problems by providing a reusable diffusion coating mask which provides a higher level of protection, which does not interact with the substrate surface even at higher coating temperatures or relatively longer coating cycles, and which minimises consumables, depositing and removal costs.

It has now been found that incorporating a metal or metal alloy into a silica-based ceramic material prevents the siliconisation problem encountered with the previously used plain ceramic caps. This enables the masks to be used at higher temperatures or over longer coating cycles. The metal or alloy used is also capable of reacting with the metallic coating vapours being applied thereby preventing diffusion coating in areas of a substrate protected by such material. The finding that the metal or alloy is able to prevent both siliconisation and diffusion coating is central to the present invention.

Accordingly, the present invention provides a mask suitable for protecting a portion of a substrate surface against diffusion coating of the substrate by metallic vapours during a pack or vapour coating process. This mask comprises a composite material containing silica and an inert refractory diluent and a metal or metal alloy, wherein the metal or metal alloy is one which is capable of reacting with silicon thereby preventing siliconisation of the substrate with silicon from the composite material under conditions of diffusion coating and which is capable of reacting with the metal being applied by diffusion coating thereby preventing diffusion coating of the portion of the substrate surface it is desired to protect.

The composite material usually contains between 5 and 50% by weight metal or metal alloy based on the total weight of the composite material. In a preferred embodiment, the amount of metal or metal alloy is between 10 and 20% by weight. Single metals or metal alloys may be used, or mixtures of different metals and/or metal alloys. When mixtures are used, the total amount of metal and/or metal alloy generally falls within these limits.

The metal or metal alloy is usually present in the ceramic matrix in the form of particles. The particles may vary in size from fine powders to granules depending upon application. Typically, the particles range between 25 and 150 microns. Particles of 75 microns or finer are typically used.

Examples of metals which may be used in practice of the present invention include nickel, cobalt, chromium, molybdenum and tungsten. Of these, the use of nickel or cobalt is preferred, particularly nickel.

Useful metal alloys which may be used include alloys based on combinations
5 of the following metals: nickel, cobalt, chromium, aluminium, molybdenum, tungsten, vanadium, tantalum, titanium and hafnium. Of these, the use of nickel-chromium alloys is preferred.

The composite material is a ceramic which contains silica and an inert refractory diluent. The latter prevents sintering to the surface being masked.
10 Refractory diluents of alumina, aluminosilicates and feldspar (plus trace elements) are typically employed. The use of alumina is preferred. The silica is usually present in the composite material (i.e. excluding the metal or metal alloy) in an amount of at least 5% by weight. The amount of silica does not usually exceed 30% by weight based on the weight of the composite material. More typically, the amount of silica
15 is from 10 to 15% by weight. The proportion of silica in the composite can be adjusted to optimise the structural integrity of the mask although here it will be appreciated that any variation in silicon content may require variation also in the content of metal or metal alloy required to inhibit siliconisation. Determination of the amount of metal or alloy for a particular silicon content is within the ability of
20 one skilled in the art.

In a preferred embodiment of the invention, the ceramic is an aluminosilicate. Thus, the masks may be conveniently prepared using clays. Useful clays are commercially available and include Puraflow-DM and Bentonite. As a consequence of using a clay, the ceramic will also include other compounds and minerals
25 commonly found in clays. In an embodiment of the invention the mask comprises 10 to 20% by weight nickel dispersed in an aluminosilicate ceramic matrix.

The metal or alloy in the mask must be in reduced form to ensure that it is available for reaction both with the silicon present in the composite material and with the metal which is being applied by diffusion coating. This requirement has
30 particular implications with respect to how the mask is prepared. Thus, the present invention further provides a process for preparing the mask, which process comprises mixing the metal or metal alloy with a ceramic material containing silica and an inert

refractory diluent, shaping the resultant mixture into a desired configuration to form a blank, and then either:

- (a) firing the blank in a reducing atmosphere to prevent oxidation of the metal or metal alloy; or
- 5 (b) firing the blank in an oxidising atmosphere followed by treatment in a reducing atmosphere to reduce the metal or metal alloy.

In one embodiment of this process the blank is fired in a reducing atmosphere, such as hydrogen or other reducing atmosphere. Firing typically takes place at a temperature of between 1150 and 1300°C for a period of time of from 30
10 minutes to 3 hours at temperature.

In the other embodiment of the process, the blank is initially fired in a conventional manner, i.e. without special steps to prevent oxidation of the metal or metal alloy. In this case, the initial firing typically also takes place at a temperature of between 1150 to 1300°C for a period of time of 30 minutes to 3 hours at
15 temperature. Subsequent to this firing, a conditioning treatment is then necessary in order to achieve reduction of the metal or metal alloy. This reduction may be achieved by heat-treatment in a reducing atmosphere (e.g. hydrogen or other) at a temperature of between 900 and 1200 °C for a period of at least one hour.

The conditions required to reduce the metal or metal alloy to the desired
20 extent may be determined easily. For example, this may be done on a trial and error basis by considering the effectiveness of the mask in the diffusion coating process. In this way, it is also possible to optimise the amount of metal or metal alloy which needs to be present in the mask.

In certain cases the extent to which the metal or alloy has been reduced can be
25 assessed visually as the colour of the metal or alloy changes with oxidation/reduction. For instance, when the mask contains nickel reduction leads to a colour change of the mask from green (nickel oxide) to grey (nickel). To achieve effective masking, the metal or alloy should be substantially in reduced form through the entire mask. Thus, for a nickel-containing mask, the grey colour should be
30 observed through any section of the mask.

The present invention also provides a mixture of components suitable for preparing the masks described herein. Thus, the ceramic material and metal or metal

alloy may be provided in ready to use granulate form.

Caps may be formed by conventional techniques such as wet pressing using a suitable die or by other ceramic forming methods. The caps so-formed may then be fired as described above.

5 The masks of the present invention may be used in diffusion coating of aluminium (aluminising) or chromium (chromising), more typically aluminium. The masks may be used in the coating of a variety of components but are expected to have particular usage in the diffusion coating of turbine blades, for example of jet engines, where it is desired to prevent coating of the blade root. Jet engine turbine
10 blades are typically formed from nickel-based superalloys, and when applied to such components, the metal present in the mask is usually nickel or a nickel-based alloy.

Typically, the mask is provided in the form of a cap which is fitted over the part of the substrate to be protected. Such an embodiment is illustrated in Figure 1 which shows a cap (a) fitted to the root of a jet engine turbine blade (b). In this
15 embodiment, the fit of the cap does not have to follow the exact profile of the area being protected although the cavity of the cap into which the substrate (component) fits should be as well-fitting as manufacturing constraints permit. The gap between the substrate and the cap is typically 0.5 mm or less, preferably 0.25 mm or less. If there is insufficient gap, the substrate may become wedged in the cap and thus be
20 difficult to remove without damaging the cap which is, of course, intended to be re-usable. It is important when preparing the cap for a substrate that contraction/expansion of the cap and substrate during coating be taken into account. Shrinkage of the cap during firing should also be accounted for. If the cavity of the cap as prepared is too small, this may be remedied by machining.


25 The masks of the invention may be used in conventional diffusion coating techniques. For example, aluminising may be carried out by a pack process at a temperature of from 800 to 1050°C for from 1 to 20 hours at temperature, for instance, aluminising at 875°C for 20 hours would be a typical coating cycle.

The masks of the invention have the advantage of being re-usable, and may
30 be employed on multiple occasions before their mechanical or protective integrity is diminished to below a useful level.

The basis for the present invention is the choice of a metal or metal alloy

which will react with silicon in the composite and with the metallic coating vapours. With reference to the use of nickel as metal and aluminium as the diffusion coating, the principle underlying the invention is believed to be as follows.

The aluminising operation causes dissociation of silicate bonds in the ceramic. The reaction (1) is believed to be oxidation of aluminising vapour to alumina coupled with silica reduction. The silica is then incorporated into the nickel particles forming nickel silicide (NiSi) (2). The latter reaction removes potentially active silicon from the system thereby preventing the siliconisation problem associated previously with plain ceramic masks.



Depletion of silicate bonding within the ceramic tends to reduce the strength of the mask although this is not sufficient to prevent the mask being used on several occasions with effectiveness intact.

Some surface depletion in the substrate of elements such as aluminium, chromium and titanium in the area protected by the mask may occur, but this is only to an extent similar to the use of conventional stop-off slurry techniques. This effect may be minimised by including in the ceramic material a metal alloy (e.g. Ni-Cr) at the expense of, or in addition to, pure metal.

The invention will now be illustrated by the following non-limiting examples.

Example 1

A ceramic material having the following composition (approx.) was blended with 20% by weight of 99.8% pure nickel powder, at least 40% of which passed through a 38 micron (400 mesh) sieve.

25	Alumina	84%
	Titania	0.02%
	Silica	10.7%
	Ferric oxide	0.26%
	Lime	3.14%
30	Magnesia	1.09%
	Potash	0.24%
	Soda	0.23%

The so-blended material was formed into caps designed to fit the root end of an H.P. turbine blade in MarM002 material. This was done by pressing the mixture using a die of the desired configuration. The caps were then "fired" at a temperature of 1220 °C for 2 hours at temperature. The resultant caps were coloured green due to the presence of nickel in oxidised form. The caps were subsequently treated in a reducing atmosphere (hydrogen) at a temperature of 1100 °C for one hour. The green colour changed to grey indicating reduction to nickel.

The caps were then used to protect the blade roots during pack aluminising for 20 hours at 875 °C. After removal of the caps, the metallurgy of the protected roots was analysed. No evidence of aluminising or siliconising was observed and the level of surface denudation was at least equivalent to that found using conventional stop-off slurries. Figure 2 shows the level of surface denudation on a blade surface protected with the subject invention. Figure 3 shows the level of surface denudation on a blade surface protected using a conventional slurry technique.

Example 2

Adopting the same procedure as Example 1, caps were prepared by blending a ceramic material having the composition (approx.) given below with 10% by weight of 200 mesh 99.8% pure nickel powder, at least 40% of which passed through a 38 micron (400 mesh) sieve.

20	Alumina	85.58%
	Titania	0.13%
	Silica	13.87%
	Ferric oxide	0.29%
	Lime	0.08%
25	Magnesia	0.11%
	Potash	0.36%
	Soda	0.57%

The caps were used to protect the roots of MarM002 turbine blades during aluminising at 875 °C for 20 hours. After the caps were removed and the root structure analysed, identical results to Example 1 were observed.

Example 3

Example 1 was followed to prepare caps with and without nickel addition.

Both types of cap were fired at 1220 °C for 2 hours at temperature followed by reductive conditioning at 1100 °C for 1 hour. The caps were then used as stop-offs on a CMSX4 material (a nickel-cobalt superalloy) during aluminising for 20 hours at 875 °C. After this the metallurgy of the protected surface was analysed. The caps without nickel led to substantial siliconising of the substrate surface. In contrast, no siliconising was observed for the caps containing nickel in accordance with the present invention.

Example 4

A ceramic material including nickel powder (75 micron (200 mesh) to 38 micron (400 mesh)) and having the following composition (approx.) was prepared.

	Alumina	71.31%
	Titania	0.10%
	Silica	11.55%
	Ferric oxide	0.24%
15	Lime	0.06%
	Magnesia	0.09%
	Potash	0.30%
	Soda	0.48%
	Nickel	15.87%

This composition was pressed into a cap designed to fit the root end of a MarM002 jet engine turbine blade. The cap was then fired and reduced as in Example 1. On fitting the cap to the root of the blade the gap between the wedge faces of the blade and the cap was found to be 0.25 mm.

The capped-blade was then placed in a pack aluminising retort for 20 hours at 875 °C. After this, the cap was removed and the root of the blade examined. It was clear from visual inspection that the area of the blade protected by the cap had not been aluminised or siliconised. Sections taken through the root for micro-examination confirmed this and that there was a minimum level of denudation. The same cap was re-used on a further four occasions with similarly acceptable results.

Example 5

A similar cap/blade combination to that used in Example 4 was subjected to aluminising at 1100 °C for three hours. Visual appearance again suggested that the

cap had prevented any aluminising of the root, and this was confirmed by micro-examination. There were no signs of siliconisation. There was a slight increase in surface denudation relative to Example 4, but this was to be expected in view of the higher aluminising temperature.

CLAIMS

1. A mask suitable for protecting a portion of a substrate surface against diffusion coating of the substrate by metallic vapours during a pack or vapour coating process which mask comprises a composite material containing silica and an inert refractory diluent and a metal or metal alloy, wherein the metal or metal alloy is one which is capable of reacting with silicon thereby preventing siliconisation of the substrate with silicon from the composite material under conditions of diffusion coating and which is capable of reacting with the metal being applied by diffusion coating thereby preventing diffusion coating of the portion of the substrate surface it is desired to protect.
2. A mask according to claim 1, wherein the metal or metal alloy is present in the composite material in an amount of 5 to 50% by weight based on the total weight of the mask.
3. A mask according to claim 2, wherein the metal or metal alloy is present in the ceramic in an amount of 10 to 20% by weight based on the total weight of the mask.
4. A mask according to any one of the preceding claims, wherein the metal is selected from nickel, cobalt, chromium, molybdenum and tungsten.
5. A mask according to claim 4, wherein the metal is nickel.
6. A mask according to any one of claims 1 to 3, wherein the metal alloy is an alloy based on a combination of metals selected from nickel, cobalt, chromium, aluminium, molybdenum, tungsten, vanadium, tantalum, titanium and hafnium.
7. A mask according to claim 6, wherein the metal alloy is a nickel-chromium alloy.
8. A mask according to any one of the preceding claims, wherein the inert refractory diluent comprises alumina, aluminosilicate or feldspar.
9. A mask according to claim 8, wherein the composite material comprises an aluminosilicate ceramic.
10. A mask according to any one of claims 1 to 5, which comprises from 10 to 20% by weight nickel dispersed in an aluminosilicate ceramic matrix.
11. A mask according to any one of the preceding claims in the form of a diffusion coating cap.

12. A process for preparing a mask as defined in any one of claims 1 to 10, which process comprises mixing the metal or metal alloy with a ceramic material containing silica and an inert refractory diluent material, shaping the resultant mixture into a desired configuration to form a blank, and then either:

- 5 (a) firing the blank in a reducing atmosphere to prevent oxidation of the metal or metal alloy; or
- (b) firing the blank in an oxidising atmosphere followed by treatment in a reducing atmosphere to reduce the metal or metal alloy.

10 13. A process according to claim 12, wherein the blank is in the shape of a cap.

14. A process according to claim 12 or 13, wherein in (a) the blank is fired at a temperature of from 1150 to 1300°C for from 30 minutes to 3 hours at temperature.

15 15. A process according to claim 12 or 13, wherein in (b) the blank is fired in an oxidising atmosphere at a temperature of from 1150 to 1300°C for from 30 minutes to 3 hours at temperature followed by treatment in a reducing atmosphere at a temperature of from 900 to 1200°C for a period of at least 1 hour.

20 16. A process for diffusion coating with a metal a selected portion of a substrate surface, which process comprises masking the substrate surface except for the portion to be coated with a mask as defined in any one of claims 1 to 11, subjecting the substrate to diffusion coating with the metallic vapour, and removing the mask from the substrate surface.

17. A process according to claim 16, wherein the metal which is being applied by diffusion coating is aluminium or chromium.

25 18. A process according to claim 16 or 17, wherein the substrate is a turbine blade and the portion of the blade protected against diffusion coating is the blade root.

19. Use of a mask as defined in any one of claims 1 to 11, to protect the surface of a substrate in a diffusion coating process.

30 20. A mixture suitable for use in preparing a mask as claimed in claim 1, which mixture is as defined in claim 12.

21. A mask according to claim 1 substantially as hereinbefore described

-12-

with reference to any of the foregoing Examples.

22. A process according to claim 12, substantially as hereinbefore described with reference to any of the foregoing Examples.

23. A mask according to claim 1, when prepared by a process as claimed
5 in any one of claims 12 to 15 or 22.

24. A diffusion coating process according to claim 16, substantially as hereinbefore described with reference to any of the foregoing Examples.

25. Use according to claim 19, substantially as hereinbefore described.

26. A mixture according to claim 20, substantially as hereinbefore
10 described.

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁷: C23C 10/04	A1	(11) International Publication Number: WO 00/58531 (43) International Publication Date: 5 October 2000 (05.10.00)
(21) International Application Number: PCT/GB00/01186 (22) International Filing Date: 28 March 2000 (28.03.00) (30) Priority Data: 9907244.9 29 March 1999 (29.03.99) GB <i>29 Sep 01 / 30 Nov</i> (71) Applicants (for all designated States except US): CHROMA-LLOY UNITED KINGDOM LIMITED [GB/GB]; Bramble Way, Clover Nook Industrial Estate, Somercotes, Derbyshire DE55 4RH (GB). WADE CERAMICS LIMITED [GB/GB]; Royal Works, Westport Road, Burslem, Stoke-on-Trent, Staffordshire ST6 4AP (GB). (72) Inventors; and (75) Inventors/Applicants (for US only): HARDY, Bryan, Anthony [GB/GB]; 16 Trent Lane, Kings Newton, Derby, Derbyshire DE73 1BT (GB); GODDARD, David, Arthur [GB/GB]; 22 Endon Drive, Biddulph, Stoke-on-Trent, Staffordshire ST6 8NJ (GB); SHAW, Edward, Hugh [GB/GB]; Crow Holt Farm, Basford, Leek, Staffordshire ST13 7DU (GB). (74) Agents: CRESSWELL, Thomas, Anthony et al.; J.A. Kemp & Co., 14 South Square, Gray's Inn, London WC1R 5LX (GB).		(81) Designated States: AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i>
(54) Title: STOP-OFF FOR DIFFUSION COATING ✓ (57) Abstract <p>A mask suitable for protecting a portion of a substrate surface against diffusion coating of the substrate with a metal, which mask comprises a ceramic material comprising silica and an inert refractory diluent and a metal or metal alloy, wherein the metal or metal alloy is one which is reactive with silicon thereby minimising or preventing siliconisation of the substrate with silicon in the ceramic material under conditions of diffusion coating, and which is reactive with the metal being applied by diffusion coating thereby preventing diffusion coating of the portion of the substrate surface it is desired to protect.</p>		

1/2

Fig.1.





Fig.2.



19-06-2000

00914270.4 - GB00/01186

09937545 .01220278


ISA-DRAW26

PCT/GB 00 / U 1 1 8 6

05 JUNE 2000

2/2

Fig.3.



PTO/SB/01 (03-01)


Approved for use through 10/31/2002 OMB 0651-0032

U.S. Patent and Trademark Office, U.S. DEPARTMENT OF COMMERCE

Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it contains a valid OMB control number

DECLARATION — Utility or Design Patent Application

Direct all correspondence to: <input type="checkbox"/> Customer Number or Bar Code Label		OR <input checked="" type="checkbox"/> Correspondence address below	
Name <u>Mitchell D. Bittman</u>			
Address <u>Sequa Corporation, Patent Dept, 3 University Plaza</u>			
City <u>Hackensack</u>	State <u>NJ</u>	ZIP <u>07601</u>	
Country <u>USA</u>	Telephone <u>201-343-1122</u>	Fax <u>201-488-2014</u>	
I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under 18 U.S.C. 1001 and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.			
NAME OF SOLE OR FIRST INVENTOR:		<input type="checkbox"/> A petition has been filed for this unsigned inventor	
Given Name (first and middle (if any)) <u>Bryan Anthony</u>		Family Name or Surname <u>Hardy</u>	
Inventor's Signature <u>B. Hardy</u>		Date <u>30-11-01</u>	
Residence: City <u>Kings Newton, Derby</u>	State <u>Derbyshire</u>	Country <u>GBN</u>	Citizenship <u>GB</u>
Mailing Address <u>16 Trent Lane</u>			
City <u>Kings Newton, Derby</u>	State <u>Derbyshire</u>	ZIP <u>DE731BT</u>	Country <u>GB</u>
NAME OF SECOND INVENTOR:		<input type="checkbox"/> A petition has been filed for this unsigned inventor	
Given Name (first and middle (if any)) <u>David Arthur</u>		Family Name or Surname <u>Goddard</u>	
Inventor's Signature <u>DA Goddard</u>		Date <u>26/11/01</u>	
Residence: City <u>Biddulph, Stoke-on-Trent</u>	State <u>Staffordshire</u>	Country <u>GBN</u>	Citizenship <u>GB</u>
Mailing Address <u>22 Endon Drive</u>			
City <u>Biddulph, Stoke-on-Trent</u>	State <u>Staffordshire</u>	ZIP <u>ST6 8NJ</u>	Country <u>GB</u>
<input checked="" type="checkbox"/> Additional inventors are being named on the supplemental Additional Inventor(s) sheet(s) PTO/SB/02A attached hereto.			



Approved for use through 10/31/2002. OMB 0651-0032
U.S. Patent and Trademark Office; U.S. DEPARTMENT OF COMMERCE
Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it contains a valid OMB control number.

**DECLARATION FOR UTILITY OR
DESIGN
PATENT APPLICATION
(37 CFR 1.63)**

☐ Declaration
Submitted
with Initial
Filing

OR

☐ Declaration
Submitted after Initial
Filing (surcharge
(37 CFR 1.16 (e))
required)

Attorney Docket Number CUK-051

First Named Inventor Hardy et al.

COMPLETE IF KNOWN

Application Number 09 / 937545

Filing Date September 26, 2001

Group Art Unit

Examiner Name

As a below named inventor, I hereby declare that:

My residence, mailing address, and citizenship are as stated below next to my name.

I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled:

STOP-OFF FOR DIFFUSION COATING

(Title of the invention)

the specification of which

☐ is attached hereto

OR

☒ was filed on (MM/DD/YYYY) September 26, 2001 as United States Application Number or PCT International

Application Number 09/937545 and was amended on (MM/DD/YYYY) September 26, 2001 (if applicable).

I hereby state that I have reviewed and understand the contents of the above identified specification, including the claims, as amended by any amendment specifically referred to above.

I acknowledge the duty to disclose information which is material to patentability as defined in 37 CFR 1.56, including for continuation-in-part applications, material information which became available between the filing date of the prior application and the national or PCT international filing date of the continuation-in-part application.

I hereby claim foreign priority benefits under 35 U.S.C. 119(a)-(d) or (f), or 365(b) of any foreign application(s) for patent, inventor's or plant breeder's rights certificate(s), or 365(a) of any PCT international application which designated at least one country other than the United States of America, listed below and have also identified below, by checking the box, any foreign application for patent, inventor's or plant breeder's rights certificate(s), or any PCT international application having a filing date before that of the application on which priority is claimed.

Prior Foreign Application Number(s)	Country	Foreign Filing Date (MM/DD/YYYY)	Priority Not Claimed	Certified Copy Attached?	
				YES	NO
PCT/GB00/01186 9907244.9	PCT GB	03/29/99	<input type="checkbox"/>	<input type="checkbox"/>	<input checked="" type="checkbox"/>
			<input type="checkbox"/>	<input type="checkbox"/>	<input checked="" type="checkbox"/>
			<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
			<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>

☐ Additional foreign application numbers are listed on a supplemental priority data sheet PTO/SB/02B attached hereto:

(Page 1 of 2)

Burden Hour Statement: This form is estimated to take 21 minutes to complete. Time will vary depending upon the needs of the individual case. Any comments on the amount of time you are required to complete this form should be sent to the Chief Information Officer, U.S. Patent and Trademark Office, Washington, DC 20231. DO NOT SEND FEES OR COMPLETED FORMS TO THIS ADDRESS. SEND TO: Assistant Commissioner for Patents, Washington, DC 20231.

Please type a plus sign (+) inside this box → ☐

PTO/GB/02A (11-00)

Approved for use through 10/31/2002. OMB 0651-0032

U.S. Patent and Trademark Office, U.S. DEPARTMENT OF COMMERCE

Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it contains a valid OMB control number.

DECLARATION

ADDITIONAL INVENTOR(S)
Supplemental Sheet

Page ___ of ___

Name of Additional Joint Inventor, if any:		<input type="checkbox"/> A petition has been filed for this unsigned inventor	
Given Name (first and middle (if any))		Family Name or Surname	
Edward Hugh		Shaw	
Inventor's Signature <i>E. H. Shaw</i>		Date 27/11/01	
Residence: City Basford, Leek	Staffordshire State	GB Country	GB Citizenship
Mailing Address Crow Holt Farm			
Mailing Address			
City Basford, Leek	Staffordshire State	ST13 7DU ZIP	GB Country
Name of Additional Joint Inventor, if any:		<input type="checkbox"/> A petition has been filed for this unsigned inventor	
Given Name (first and middle (if any))		Family Name or Surname	
Inventor's Signature		Date	
Residence: City	State	Country	Citizenship
Mailing Address			
Mailing Address			
City	State	ZIP	Country
Name of Additional Joint Inventor, if any:		<input type="checkbox"/> A petition has been filed for this unsigned inventor	
Given Name (first and middle (if any))		Family Name or Surname	
Inventor's Signature		Date	
Residence: City	State	Country	Citizenship
Mailing Address			
Mailing Address			
City	State	ZIP	Country

Burden Hour Statement: This form is estimated to take 21 minutes to complete. Time will vary depending upon the needs of the individual case. Any comments on the amount of time you are required to complete this form should be sent to the Chief Information Officer, U.S. Patent and Trademark Office, Washington, DC 20231. DO NOT SEND FEES OR COMPLETED FORMS TO THIS ADDRESS. SEND TO: Assistant Commissioner for Patents, Washington, DC 20231.

Please type a plus sign (+) inside this box



PTO/SB/81 (02-01)
Approved for use through 10/31/2002. OMB 0651-0035

Under the Paperwork Reduction Act of 1995, no person is required to respond to a collection of information unless it displays a valid OMB control number.

POWER OF ATTORNEY OR AUTHORIZATION OF AGENT

Application Number	09/937545
Filing Date	September 26, 2001
First Named Inventor	Hardy et al.
Title	Stop-Off For Diffusion Coating
Group Art Unit	
Examiner Name	
Attorney Docket Number	CUK-051

I hereby appoint:

☐ Practitioners at Customer Number

Place Customer
Number Bar Code
Label here

OR

☒ Practitioner(s) named below:

Name	Registration Number
Mitchell D. Bittman	27,517

as my/our attorney(s) or agent(s) to prosecute the application identified above, and to transact all business in the United States Patent and Trademark Office connected therewith.

Please change the correspondence address for the above-identified application to:

☐ The above-mentioned Customer Number.

OR

☐ Practitioners at Customer Number

Place Customer
Number Bar Code
Label here

☒ Firm or
Individual Name

Address					Sequa Corporation, Patent Department						
Address					3 University Plaza						
City		Hackensack		State		NJ		Zip		07601	
Country					USA						
Telephone					201-343-1122			Fax		201-488-2014	

I am the:

☒ Applicant/Inventor.

☐ Assignee of record of the entire interest. See 37 CFR 3.71.
Statement under 37 CFR 3.73(b) is enclosed. (Form PTO/SB/96).

SIGNATURE of Applicant or Assignee of Record

Name	Bryan Anthony Hardy
Signature	
Date	

NOTE: Signatures of all the inventors or assignees of record of the entire interest or their representative(s) are required. Submit multiple forms if more than one signature is required, see below*.

☒ *Total of 3 forms are submitted.

Burden Hour Statement: This form is estimated to take 3 minutes to complete. Time will vary depending upon the needs of the individual case. Any comments on the amount of time you are required to complete this form should be sent to the Chief Information Officer, U.S. Patent and Trademark Office, Washington, DC 20231. DO NOT SEND FEES OR COMPLETED FORMS TO THIS ADDRESS. SEND TO: Assistant Commissioner for Patents, Washington, DC 20231.


Please type a plus sign (+) inside this box → ☐

PTO/SB/81 (02-01)

Approved for use through 10/31/2002. OMB 0651-0035

U.S. Patent and Trademark Office; U.S. DEPARTMENT OF COMMERCE

Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it displays a valid OMB control number.



POWER OF ATTORNEY OR AUTHORIZATION OF AGENT

Application Number	09/937545
Filing Date	September 26, 2001
First Named Inventor	Hardy et al.
Title	Stop-Off For Diffusion Coating
Group Art Unit	
Examiner Name	
Attorney Docket Number	CUK-051

I hereby appoint:

☐ Practitioners at Customer Number

OR

☒ Practitioner(s) named below:

Name	Registration Number
Mitchell D. Bittman	27,517

Place Customer
Number Bar Code
Label here

as my/our attorney(s) or agent(s) to prosecute the application identified above, and to transact all business in the United States Patent and Trademark Office connected therewith.

Please change the correspondence address for the above-identified application to:

☐ The above-mentioned Customer Number.

OR

☐ Practitioners at Customer Number

OR

Place Customer
Number Bar Code
Label here

☒ Firm or
Individual Name

Address	Sequa Corporation, Patent Department				
Address	3 University Plaza				
City	Hackensack	State	NJ	Zip	07601
Country	USA				
Telephone	201-343-1122	Fax	201-488-2014		

I am the:

☒ Applicant/Inventor.

☐ Assignee of record of the entire interest. See 37 CFR 3.71.
Statement under 37 CFR 3.73(b) is enclosed. (Form PTO/SB/96).

SIGNATURE of Applicant or Assignee of Record

Name	Edward Hugh Shaw				
Signature	X <i>EH Shaw</i>				
Date	27/11/01				

NOTE: Signatures of all the inventors or assignees of record of the entire interest or their representative(s) are required. Submit multiple forms if more than one signature is required, see below*.

*Total of 3 forms are submitted.

Burden Hour Statement: This form is estimated to take 3 minutes to complete. Time will vary depending upon the needs of the individual case. Any comments on the amount of time you are required to complete this form should be sent to the Chief Information Officer, U.S. Patent and Trademark Office, Washington, DC 20231. DO NOT SEND FEES OR COMPLETED FORMS TO THIS ADDRESS. SEND TO: Assistant Commissioner for Patents, Washington, DC 20231.

☐ Page(s) _____ of _____ were not present
for scanning. (Document title)

☐ Page(s) _____ of _____ were not present for scanning. (Document title)

Scanned copy is best available. THE DRAWINGS ARE DARK